

CHROMALUXE ALUMINUM PHOTO PANELS

Guidelines for Swing-Away 16x20 Heat Press with Nomex Pad

The following guidelines represent the best, most general instructions we can provide. However, please remember that heat presses may vary.

Please check with your manufacturer for any special concerns.

This information may change as we make continual improvements and refine our processes.

16X20 PRESS

ITEM	TEMP.	TIME	QTY	SPECIAL NOTES
4x4	400°F	1:00-1:05	4+	
4x6, 5x5	400°F	1:00-1:05	1	
5x7, 6x6	400°F	1:10-1:15	1	
8x8, 8x10, 5x10, 10x10	400°F	1:25-1:30	1	
11x11, 12x12	400°F	1:30-1:35	1	
11x14	400°F	1:45-1:50	1	Must use Endura Fabric
11x17	400°F	1:40-1:45	1	Must use Endura Fabric
9x21, 10x20, 12x18, 16x16	400°F	1:50-1:55	1	Must use Endura Fabric
16x20	400°F	2:00-2:05	1	Must use Endura Fabric
AL. CIRCLE 8"	400°F	1:20-1:25	1	
AL. CIRCLE 11"	400°F	1:25-1:30	1	
AL. CIRCLE 16"	400°F	1:30-1:35	1	

CHROMALUXE MDF PHOTO PANELS

Guidelines for using a 16x20 Heat Press with Nomex Pad

The following guidelines represent the best, most general instructions we can provide. However, please remember that heat presses may vary. Please check with your manufacturer for any special concerns.

16X20 PRESS

ITEM	TEMP.	TIME	QTY	SPECIAL NOTES
8x10	400°F	1:35-1:40	1	
9x18, 11x14, 11.6x11.6	400°F	2:00-2:05	1	Must use Endura Fabric
16x20	400°F	2:10-2:15	1	Must use Endura Fabric

CHROMALUXE THB PHOTO PANELS

Guidelines for using a 16x20 Heat Press with Nomex Pad

The following guidelines represent the best, most general instructions we can provide. However, please remember that heat presses may vary. Please check with your manufacturer for any special concerns.

16X20 PRESS

ITEM	TEMP	TIME	QTY	SPECIAL NOTES
5x7	400°F	1:25-1:30	1	
3.5x5	400°F	1:15-1:20	1	
6x6	400°F	1:25-1:30	1	
7.87x11.81, 8x10	400°F	1:35-1:40	1	
10x10	400°F	1:40-1:45	1	

CHROMALUXE NATURAL WOOD PHOTO PANELS

Guidelines for using a 16x20 Heat Press with Nomex Pad

The following guidelines represent the best, most general instructions we can provide. However, please remember that heat presses may vary. Please check with your manufacturer for any special concerns.

16X20 PRESS

ITEM	TEMP.	TIME	QTY	SPECIAL NOTES
8x8, 8x10, 10x10	400°F	1:45-1:50	1	
11x14	400°F	1:50-1:55	1	
16x20	400°F	1:55-2:00	1	